

Where the lithium goes

Inside a BASF battery-recycling disclosure: follow the lithium-bearing stream, decode the original process drawing, and separate the core claim from the optional steps.

01 / The first destination is a liquid.

The core process contacts battery material with a specified hypochlorite-containing aqueous medium, then separates solids from liquids. Its immediate lithium product is an aqueous solution, rather than a finished new battery material.

[Source page 10](#)

02 / The diagram goes further than the core claim.

The pictured route continues through purification, possible conversion to lithium hydroxide and crystallization. Those downstream choices should not all be read as requirements of independent claim 1.

[Source page 6](#) · [Source page 10](#)

03 / Nickel and cobalt are a boundary, not a second result.

They can occur in the starting material. This disclosure does not establish a separate nickel-versus-cobalt recovery process. Its principal reading is lithium liberation and purification.

[Source page 3](#) · [Source page 4](#) · [Source page 10](#)

The complete explanation follows, with annotated source drawings and all 11 original pages. Blue source references work inside this PDF.

The problem and central idea

A lithium-first separation process

The disclosure concerns recovery of lithium from battery-derived material, including mechanically produced “black mass.” Its central process is to contact the material with an aqueous medium containing calcium hypochlorite, lithium hypochlorite, or a combination of those salts, then separate solids from liquids. The required immediate output is an aqueous solution containing lithium ions. In the description’s proposed calcium-hypochlorite reaction pathway, lithium from a lithium metal oxide is liberated into a lithium-chloride-containing liquid while much calcium is associated with sparingly soluble calcium hydroxide. Thus, the principal objective is to move lithium into a liquid stream that can be purified further.

[Source page 3](#) · [Source page 5](#)

Nickel and cobalt are not individually separated here

Nickel and cobalt may be present in the starting material, notably in lithiated nickel-cobalt-manganese and nickel-cobalt-aluminum oxides. However, the disclosure does not describe a distinct nickel-versus-cobalt separation step, a nickel product, or a cobalt product. Its stated focus is lithium removal and purification. The examples report an observation that calcium hypochlorite maintained pH at a level said to avoid dissolution of base metals while allowing the reaction to continue. That observation does not establish the individual destinations of nickel or cobalt, nor does it demonstrate their separation from one another.

[Source page 3](#) · [Source page 4](#) · [Source page 10](#)

The important parts, entities or structures

Black mass and optional preparation

Black mass is battery-derived material made by mechanical processing such as comminution. It may contain graphite and cathode active material, together with impurities from casings, electrode foils, cables, separators, and electrolyte. The description permits disassembly, shredding, milling, and removal of light fractions before the aqueous treatment. Solvent removal of polymeric binders and heat treatment are further described options, rather than universal steps. The stated heat-treatment range is 100°C to 900°C, but the description cautions that above 400°C some transition-metal oxides may be reduced and their inorganic composition may change. One described way to avoid reduction is to remain below 400°C and/or remove carbonaceous material first.

[Source page 4](#)

The streams created by the process

The chemical contact is the lithium-liberation stage. Solid/liquid separation then divides the reaction slurry into a lithium-bearing liquid and a solid residue. The description identifies insoluble black-mass residues such as graphite and solid calcium hydroxide as material that may be present in that residue. The liquid can then undergo lithium/calcium separation, with calcium species removed by nanofiltration, precipitation, crystallization, solvent exchange, ion exchange, or combinations. A lithium/sodium separation is separately described for cases where sodium ions are to be removed. These liquor-purification stages address lithium, calcium, sodium, and other impurities; they are not disclosed as cobalt/nickel splitting operations.

[Source page 5](#) · [Source page 6](#)

How the described mechanism or process works

One main route. Two visible side outputs.




FIG. 1

Original FIG. 1, process 100. The patent supplies the numbers and arrows; paragraph [0064] supplies the operation names. The pictured chain is exemplary. Blue numbered leaders identify parts and do not add process connections.

01 / 101 / Aqueous treatment — Start the lithium-liberation step

The exemplary route treats battery material in an aqueous medium containing calcium hypochlorite. Claim 1 also permits lithium hypochlorite or their combination.

[Source page 6](#) · [Source page 10](#)

03 / 103 → 109 / Li-Ca separation — Remove calcium from the liquid stream

The text identifies 103 as lithium/calcium separation and 109 as a collected calcium salt. It lists alternative separation techniques.

[Source page 6](#)

05 / 105 / Transformation — Possible conversion to lithium hydroxide

The text offers reaction with calcium hydroxide, LiCl electrolysis or electrodialysis. The box does not mean all alternatives are performed.

[Source page 6](#)

02 / 102 → 108 / Solid-liquid split — Separate the lithium-bearing liquid

The side output 108 is a lithium-depleted solid residue. The lithium-containing liquid continues toward 103.

[Source page 6](#)

04 / 104 / Li-Na separation — A further purification option

The lithium salt solution may undergo a separate lithium/sodium separation. This downstream choice is not required by independent claim 1.

[Source page 6](#) · [Source page 10](#)

06 / 106 → 107 / Crystallization and output — Reach a lithium-salt product

Crystallization may yield a lithium salt such as lithium hydroxide monohydrate. This is a downstream example beyond the core liquid-producing split.

[Source page 6](#)

The original process, decoded

Original Figure 1 on page 2 can be read alongside paragraph [0064]. The numbered boxes and two side outlets form an exemplary process, not a statement that every downstream step is required. Process (100) starts with treatment in an aqueous medium containing calcium hypochlorite (101). The arrow leads to solid-liquid separation (102), with a side outlet (108) identified in the description as a lithium-depleted solid residue that may contain calcium salts. The main path continues downward to Li/Ca separation (103). Its side outlet (109) is identified as a calcium salt. The downward path then passes through Li/Na separation (104), potential conversion to LiOH (105), crystallization (106), and lithium-salt output (107). Paragraph [0064] supplies these names and qualifications; the original drawing itself mainly shows numbers and arrows. The following section explains the optional downstream choices. This additional original-sheet inspection was performed by Codex after the automatic review, which had only received the textual description.

[Source page 6](#)

Downstream lithium branches and reported evidence

After Li/Ca separation (103), the exemplary route says the lithium salt solution may undergo Li/Na separation (104), such as precipitation as carbonate, solvent extraction, adsorption, or ion exchange. It may then be transformed to LiOH at (105), for example by reaction with calcium hydroxide, LiCl electrolysis, or electrodialysis. Crystallization (106) may yield a lithium salt such as LiOH·H₂O at (107). If LiCl electrolysis is used, chlorine may optionally be recycled to produce calcium hypochlorite; recovered calcium hydroxide may also be used to make chlorinated lime. These are alternatives and additional embodiments, not a single mandatory chain. The examples and discussion report comparative observations favoring calcium hypochlorite over sodium hypochlorite or ammonium persulfate for lithium recovery and pH behavior. They do not provide evidence that the process was industrially deployed, and they do not quantify an environmental benefit.

[Source page 6](#) · [Source page 10](#)

Important claim wording and dependencies

What independent claim 1 requires

Claim 1 has two core requirements. First, battery material is contacted with an aqueous medium containing at least one salt selected from calcium hypochlorite, lithium hypochlorite, and combinations of them, forming a mixture. Second, solids are separated from liquids in that mixture to obtain an aqueous solution comprising lithium ions. The wording permits calcium hypochlorite alone, lithium hypochlorite alone, or a combination; it does not require both salts. Claim 1 does not itself require mechanical comminution, a stated temperature or duration, Li/Ca separation, Li/Na separation, electrolysis, crystallization, calcium recovery, or a nickel/cobalt separation.

[Source page 10](#)

Dependent claims and the separate recycling claim

Claims 2–7 add material choices and compositions. Claims 8–10 add a calcium-hypochlorite-to-material ratio, a contacting temperature/time, or specified physical separation techniques. Claims 11–15 add purification, chlor-alkali electrolysis, use of its chlorine, calcium-hydroxide recovery, and use of recovered calcium hydroxide to make chlorinated lime. Each is a dependent addition to the claim it names: claim 15 depends on claim 14, so it includes calcium-hydroxide recovery before its stated use. Claims 19–21 add initial, final, or during-contact pH limits. Independent claim 16 is distinct from claim 1 because it requires mechanical comminution of specified battery inputs to obtain black mass before aqueous hypochlorite contact and solids/liquids separation. Claim 18 depends on claim 13 and further requires reuse of chlorinated lime and/or lithium hypochlorite produced from electrolysis-derived chlorine.

[Source page 10](#) · [Source page 11](#)

Answers on separations, lithium destination, and optional choices

What each main separation accomplishes and where lithium ends up

Mechanical processing can prepare black mass, but is an express requirement only of claim 16. Hypochlorite contact is intended to liberate lithium into the aqueous phase. Solid/liquid separation is the decisive first split: it produces lithium-ion-containing liquid and a lithium-depleted solid residue that may include graphite and calcium hydroxide. Li/Ca separation then improves the lithium stream by removing calcium species and collecting a calcium salt. Li/Na separation is a further, separate option when sodium removal is wanted. Conversion and crystallization may take the purified lithium stream toward lithium hydroxide and, in the textual exemplary route, $\text{LiOH} \cdot \text{H}_2\text{O}$. No stated operation performs a separate nickel-from-cobalt split.

[Source page 5](#) · [Source page 6](#)

Essential choices versus optional embodiments

For claim 1, the required steps are contacting the battery material with an aqueous medium comprising at least one of calcium hypochlorite, lithium hypochlorite, or their combinations, and separating solids from liquids to obtain an aqueous solution comprising lithium ions. For claim 16, mechanically comminuting specified battery-related material to obtain black mass is additionally required. Calcium hypochlorite is an alternative permitted by claim 1 and is specifically required by dependent claim 17; it is not required for every claim 1 embodiment because lithium hypochlorite and combinations of the two are also recited. The 20 °C to 100 °C contact temperature, 10-minute to 10-hour duration, and specified separation equipment are dependent-claim limitations. Purification, chlor-alkali electrolysis, and calcium-hydroxide recovery or reuse are also claimed in dependent claims. Li/Ca separation (103) and Li/Na separation (104) are described optional embodiments or exemplary-route operations, not dependent-claim features. The textual exemplary route is treatment (101), solid-liquid separation (102), Li/Ca separation (103), optionally Li/Na separation (104), potential transformation to LiOH (105), crystallization (106), and lithium-salt output (107), with side outputs (108) and (109).

[Source page 3](#) · [Source page 6](#) · [Source page 10](#)

Sources and review

One publication; all nine identified description and claim pages supplied to the explanation. Six annotations on the original drawing. All eleven original pages follow, unchanged.

The automated review supported the ten text blocks but could not inspect Figure 1. Codex subsequently checked original page 2 against paragraph [0064] on page 6, and inspected this edition's annotations and layout. The original automated verdict is preserved; this was assisted review, not independent human review.

Independent research about this patent; its organization is a subject of research, not a claimed customer or endorser.



US 20240347801A1

(19) **United States**

(12) **Patent Application Publication**
Rohde et al.

(10) **Pub. No.: US 2024/0347801 A1**

(43) **Pub. Date: Oct. 17, 2024**

(54) **PROCESS FOR RECYCLING LITHIUM ION
BATTERY MATERIALS**

Publication Classification

(71) Applicant: **BASF SE**, Ludwigshafen am Rhein
(DE)

(72) Inventors: **Wolfgang Rohde**, Ludwigshafen (DE);
Dieter G Von Deak, Beachwood, OH
(US); **Birgit Gerke**, Ludwigshafen
(DE)

(73) Assignee: **BASF SE**, Ludwigshafen am Rhein
(DE)

(51) **Int. Cl.**

H01M 10/54 (2006.01)

C22B 3/22 (2006.01)

C22B 7/00 (2006.01)

C22B 26/12 (2006.01)

C25B 1/26 (2006.01)

(52) **U.S. Cl.**

CPC **H01M 10/54** (2013.01); **C22B 3/22**

(2013.01); **C22B 7/005** (2013.01); **C22B 7/006**

(2013.01); **C22B 26/12** (2013.01); **C25B 1/26**

(2013.01)

(21) Appl. No.: **18/579,698**

(22) PCT Filed: **Jul. 22, 2022**

(86) PCT No.: **PCT/EP2022/070700**

§ 371 (c)(1),

(2) Date: **Jan. 16, 2024**

(30) **Foreign Application Priority Data**


Jul. 23, 2021 (EP) 21187550.5

(57)

ABSTRACT

Disclosed herein are processes for removing lithium from a battery material comprising contacting the battery material with an aqueous medium comprising calcium hypochlorite salts to form a mixture, and separating in the mixture solids from liquids to obtain an aqueous solution comprising lithium ions. Also disclosed are processes for recycling lithium ion battery materials.

100






FIG. 1

PROCESS FOR RECYCLING LITHIUM ION BATTERY MATERIALS

[0001] The project leading to this application has received funding from the European Union's Horizon 2020 research and innovation programme under Specific Grant Agreement No EIT/RAW MATERIALS/SGA2020/1, Project Agreement No. 19211.

[0002] Disclosed herein are processes for removing lithium from a battery material comprising contacting the battery material with an aqueous medium comprising at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof to form a mixture, and separating in the mixture solids from liquids to obtain an aqueous solution comprising lithium ions. Also disclosed are processes for recycling lithium ion battery materials.

[0003] Lithium ion battery materials are a valuable source of lithium. The removal of lithium from a battery material is an important step for recycling lithium ion battery materials. Lithium ion battery materials are complex mixtures of various elements and compounds, and it may be desirable to separate various non-lithium impurities. Removal of lithium from a battery material using, e.g., sodium hypochlorite may result in a self-quenching pH increase and may provide unsatisfactory lithium recovery and/or unsatisfactory lithium purity.

[0004] Accordingly, there is a need for processes for removing lithium from a battery material and processes for recycling lithium ion battery materials. For example, there is a need for economic processes with high lithium recovery and high lithium purity.

[0005] Disclosed herein are processes for removing lithium from a battery material comprising contacting the battery material with an aqueous medium comprising at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof to form a mixture, and separating in the mixture solids from liquids to obtain an aqueous solution comprising lithium ions.

[0006] In some embodiments, the battery material comprises at least one chosen from lithiated nickel cobalt manganese oxide, lithiated nickel cobalt aluminum oxide, lithium metal phosphate, lithium ion battery scrap, and black mass derived from a lithium ion battery.

[0007] In some embodiments, the battery material comprises lithium metal phosphate of formula Li_xMPO_4 wherein x is an integer greater than or equal to one, and M is chosen from metals, transition metals, rare earth metals, and combinations thereof.

[0008] In some embodiments, the battery material comprises lithiated nickel cobalt manganese oxide of formula $\text{Li}_{1+x}(\text{Ni}_a\text{Co}_b\text{Mn}_c\text{M}^1_d)_{1-x}\text{O}_2$, wherein M^1 is chosen from Mg, Ca, Ba, Al, Ti, Zr, Zn, Mo, V and Fe, $0 \leq x \leq 0.2$, $0.1 \leq a \leq 0.95$, $0 \leq b \leq 0.9$ (such as $0.05 < b \leq 0.5$), $0 \leq c \leq 0.6$, $0 \leq d \leq 0.1$, and $a+b+c+d=1$.

[0009] In some embodiments, the battery material comprises lithiated nickel-cobalt aluminum oxides of formula $\text{Li}[\text{Ni}_h\text{Co}_i\text{Al}_j]\text{O}_{2+p}$, wherein h ranges from 0.8 to 0.90, i ranges from 0.1 to 0.3, j ranges from 0.01 to 0.10, and r ranges from zero to 0.4.

[0010] In some embodiments, the battery material comprises nickel, cobalt, manganese, copper, aluminum, iron, phosphorus, or combinations thereof.

[0011] In some embodiments, wherein the battery material has a weight ratio ranging from 0.01 to 10 of lithium to a total weight of nickel, cobalt, manganese, copper, alumi-

num, iron, and phosphorus. In some embodiments, wherein the battery material has a weight ratio ranging from 0.01 to 5 of lithium to a total weight of nickel, cobalt, manganese, copper, aluminum, iron, and phosphorus. In some embodiments, wherein the battery material has a weight ratio ranging from 0.01 to 2 of lithium to a total weight of nickel, cobalt, manganese, copper, aluminum, iron, and phosphorus. In some embodiments, wherein the battery material has a weight ratio ranging from 0.01 to 1 of lithium to a total weight of nickel, cobalt, manganese, copper, aluminum, iron, and phosphorus.

[0012] In some embodiments, at the contacting step, a weight ratio of the at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof to a total weight of the battery material ranges from 0.1 to 100.

[0013] In some embodiments, the contacting step is at a temperature ranging from 20° C. to 100° C. for a duration ranging from 10 minutes to 10 hours.

[0014] In some embodiments, the separating step comprises at least one process chosen from filtration, decantation, centrifugation, sedimentation and combinations thereof to separate the solids from the liquids.

[0015] In some embodiments, the process further comprises purifying the aqueous solution comprising lithium ions by at least one process chosen from adsorption, ion exchange, precipitation, crystallization, nanofiltration, concentration by water removal, drowning-out crystallization, re-dissolution of a lithium salt in an organic solvent, and combinations thereof.

[0016] In some embodiments, the process further comprises subjecting the aqueous solution comprising lithium ions to a chlor-alkali-electrolysis process to obtain lithium hydroxide and chlorine gas.

[0017] In some embodiments, the chlorine gas is used to produce chlorinated lime and/or lithium hypochlorite.

[0018] In some embodiments, the chlorinated lime and/or lithium hypochlorite produced from the chlorine gas obtained from the chlor-alkali-electrolysis is used for removing lithium from a battery material.

[0019] In some embodiments, calcium hydroxide is recovered from the solids.

[0020] In some embodiments, the calcium hydroxide is used to produce chlorinated lime.

[0021] Also disclosed herein are processes for recycling lithium ion battery materials comprising mechanically comminuting at least one chosen from a lithium ion battery, lithium ion battery waste, lithium ion battery production scrap, lithium ion cell production scrap, lithium ion cathode active material, and combinations thereof to obtain a black mass, contacting the black mass with an aqueous medium comprising at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof, and separating solids from liquids to obtain an aqueous solution comprising lithium ions.

BRIEF DESCRIPTION OF THE DRAWINGS

[0022] FIG. 1 depicts an exemplary process for removing lithium from a battery material and/or an exemplary process for recycling lithium ion battery materials.

DEFINITIONS

[0023] As used herein, “a” or “an” entity refers to one or more of that entity, e.g., “a compound” refers to one or more compounds or at least one compound unless stated otherwise. As such, the terms “a” (or “an”), “one or more”, and “at least one” are used interchangeably herein.

[0024] As used herein, the term “material” refers to the elements, constituents, and/or substances of which something is composed or can be made.

[0025] As used herein, the term “chlor-alkali-electrolysis” refers to a process for producing chlorine gas from a liquid or solution comprising chloride ions by electrolysis.

[0026] As used herein, the term “electrolysis” refers to the chemical decomposition produced by passing an electric current through a liquid or solution comprising ions.

[0027] As used herein, the term “chlorinated lime” refers to a mixture of calcium chloride, calcium hydroxide, and calcium hypochlorite.

Black Mass:

[0028] “Black mass” refers to materials comprising lithium derived from, for example, a lithium ion battery, lithium ion battery waste, lithium ion battery production scrap, lithium ion cell production scrap, lithium ion cathode active material, and/or combinations thereof by mechanical processes such as mechanical comminution. For example, black mass may be derived from battery scrap by mechanically treating the battery scrap to obtain the active components of the electrodes such as graphite and cathode active material and may include impurities from the casing, electrode foils, cables, separator, and electrolyte. In some examples, the battery scrap may be subjected to a heat treatment to pyrolyze organic (e.g. electrolyte) and polymeric (e.g. separator and binder) materials. Such a heat treatment may be performed before or after mechanical comminution of the battery material.

[0029] Lithium ion batteries may be disassembled, punched, milled, for example in a hammer mill, and/or shredded, for example in an industrial shredder. From this kind of mechanical processing the active material of the battery electrodes may be obtained. A light fraction such as housing parts made from organic plastics and aluminum foil or copper foil may be removed, for example, in a forced stream of gas, air separation or classification.

[0030] Battery scraps may stem from, e.g., used batteries or from production waste such as off-spec material. In some embodiments a battery material is obtained from mechanically treated battery scraps, for example from battery scraps treated in a hammer mill or in an industrial shredder. Such material may have an average particle diameter (D50) ranging from 1 μm to 1 cm, such as from 1 to 500 μm , and further for example, from 3 to 250 μm .

[0031] Larger parts of the battery scrap like the housings, the wiring and the electrode carrier films may be separated mechanically such that the corresponding materials may be excluded from the battery material that is employed in the process.

[0032] Mechanically treated battery scrap may be subjected to a solvent treatment in order to dissolve and separate polymeric binders used to bind the transition metal oxides to current collector films, or, e.g., to bind graphite to current collector films. Suitable solvents are N-methylpyrrolidone, N,N-dimethyl-formamide, N,N-dimethylacetamide, N-eth-

ylpyrrolidone, and dimethylsulfoxide, in pure form, as mixtures of at least two of the foregoing, or as a mixture with 1% to 99% by weight of water.

[0033] Mechanically treated battery scrap may be subjected to a heat treatment in a wide range of temperatures under different atmospheres. The temperature range is usually in the range of 100° C. to 900° C. Lower temperatures below 300° C. may serve to evaporate residual solvents from the battery electrolyte, at higher temperatures the binder polymers may decompose while at temperatures above 400° C. the composition of the inorganic materials may change as some transition metal oxides may become reduced either by the carbon contained in the scarp material or by introducing reductive gases. In some embodiments, a reduction of lithium metal oxides may be avoided by keeping the temperature below 400° C. and/or by removing carbonaceous materials before the heat treatment.

[0034] In some embodiments, the battery material comprises at least one chosen from lithiated nickel cobalt manganese oxide, lithiated nickel cobalt aluminum oxide, lithium metal phosphate, lithium ion battery scrap, black mass derived from a lithium ion battery, and combinations there.

[0035] In some embodiments, the battery material comprises lithium metal phosphate of formula Li_xMPO_4 , wherein x is an integer greater than or equal to one, and M is chosen from metals, transition metals, rare earth metals, and combinations thereof.

[0036] In some embodiments, the battery material comprises lithiated nickel cobalt manganese oxide of formula $\text{Li}_{1+x}(\text{Ni}_a\text{Co}_b\text{Mn}_c\text{M}^1_d)_{1-x}\text{O}_2$, wherein M^1 is chosen from Mg, Ca, Ba, Al, Ti, Zr, Zn, Mo, V and Fe, $0 \leq x \leq 0.2$, $0.1 \leq a \leq 0.95$, $0 \leq b \leq 0.9$ (such as $0.05 < b \leq 0.5$), $0 \leq c \leq 0.6$, $0 \leq d \leq 0.1$, and $a+b+c+d=1$. Exemplary lithiated nickel cobalt manganese oxides include $\text{Li}_{(1+x)}[\text{Ni}_{0.33}\text{Co}_{0.33}\text{Mn}_{0.33}]_{(1-x)}\text{O}_2$, $\text{Li}_{(1+x)}[\text{Ni}_{0.5}\text{Co}_{0.2}\text{Mn}_{0.3}]_{(1-x)}\text{O}_2$, $\text{Li}_{(1+x)}[\text{Ni}_{0.6}\text{Co}_{0.2}\text{Mn}_{0.2}]_{(1-x)}\text{O}_2$, $\text{Li}_{(1+x)}[\text{Ni}_{0.7}\text{Co}_{0.2}\text{Mn}_{0.3}]_{(1-x)}\text{O}_2$, $\text{Li}_{(1+x)}[\text{Ni}_{0.8}\text{Co}_{0.1}\text{Mn}_{0.1}]_{(1-x)}\text{O}_2$ each with x as defined above, and $\text{Li}[\text{Ni}_{0.85}\text{Co}_{0.13}\text{Al}_{0.02}]\text{O}_2$.

[0037] In some embodiments, the battery material comprises lithiated nickel-cobalt aluminum oxides of formula $\text{Li}[\text{Ni}_h\text{CO}_i\text{Al}_j]\text{O}_{2+z}$, wherein h ranges from 0.8 to 0.90, i ranges from 0.1 to 0.3, j ranges from 0.01 to 0.10, and r ranges from zero to 0.4.

[0038] In some embodiments, the battery material comprises nickel, cobalt, manganese, copper, aluminum, iron, phosphorus, or combinations thereof.

[0039] In some embodiments, wherein the battery material has a weight ratio ranging from 0.01 to 10 of lithium to a total weight of nickel, cobalt, manganese, copper, aluminum, iron, and phosphorus. In some embodiments, wherein the battery material has a weight ratio ranging from 0.01 to 5 of lithium to a total weight of nickel, cobalt, manganese, copper, aluminum, iron, and phosphorus. In some embodiments, wherein the battery material has a weight ratio ranging from 0.01 to 2 of lithium to a total weight of nickel, cobalt, manganese, copper, aluminum, iron, and phosphorus. In some embodiments, wherein the battery material has a weight ratio ranging from 0.01 to 1 of lithium to a total weight of nickel, cobalt, manganese, copper, aluminum, iron, and phosphorus.

[0040] In some embodiments, the battery material comprises Li_xMO_2 wherein x is an integer greater than or equal

to one, and M is chosen from metals, transition metals, rare earth metals, and combinations thereof.

[0041] In some embodiments, a process for recycling lithium ion battery materials comprises mechanically comminuting at least one chosen from a lithium ion battery, lithium ion battery waste, lithium ion battery production scrap, lithium ion cell production scrap, lithium ion cathode active material, and combinations thereof to obtain a black mass.

Leaching:

[0042] In some embodiments, a process for removing lithium from a battery material comprises contacting the battery material with an aqueous medium comprising at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof to form a mixture. In some embodiments, a process for recycling lithium ion battery materials comprises mechanically comminuting at least one chosen from a lithium ion battery, lithium ion battery waste, lithium ion battery production scrap, lithium ion cell production scrap, lithium ion cathode active material, and combinations thereof to obtain a black mass, contacting the black mass with an aqueous medium comprising at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof.

[0043] Without wishing to be bound by theory, calcium hypochlorite may oxidize an exemplary lithium metal oxide such as LiMO_2 to liberate the lithium as lithium chloride: $4\text{LiMO}_2 + \text{Ca}(\text{ClO})_2 + \text{H}_2\text{O} \rightarrow 2\text{LiCl} + 4\text{MO}_2 + \text{Ca}(\text{OH})_2 + 2\text{LiOH}$. Using chlorinated lime of formula $3\text{CaCl}(\text{OCl}) \cdot \text{Ca}(\text{OH})_2 \cdot 5\text{H}_2\text{O}$, and noting a possible equilibrium of $2\text{LiOH} + \text{CaCl}_2 \rightleftharpoons 2\text{LiCl} + \text{Ca}(\text{OH})_2$, the reaction of chlorinated lime with a lithium metal oxide may be described by the equation: $6\text{LiMO}_2 + [3\text{CaCl}(\text{OCl}) \cdot \text{Ca}(\text{OH})_2 \cdot 5\text{H}_2\text{O}] \rightarrow 6\text{LiCl} + 6\text{MO}_2 + 4\text{Ca}(\text{OH})_2 + 2\text{H}_2\text{O}$.

[0044] Alternatively, use of sodium hypochlorite may proceed according to: $2\text{LiMO}_2 + \text{NaClO} + \text{H}_2\text{O} \rightarrow \text{LiCl} + \text{LiOH} + \text{MO}_2 + \text{NaOH}$. Since sodium hydroxide may eventually increase the pH such that the oxidation potential of the hypochlorite is reduced too much to keep the reaction going, an acid may be required to lower the pH.

[0045] Use of lithium hypochlorite may proceed according to: $2\text{LiMO}_2 + \text{LiClO} + \text{H}_2\text{O} \rightarrow \text{LiCl} + 2\text{LiOH} + \text{MO}_2$. Since lithium hydroxide may eventually increase the pH such that the oxidation potential of the hypochlorite is reduced too much to keep the reaction going, an acid may be added to lower the pH.

[0046] By contrast, the pH-value may be quasi buffered when using calcium hypochlorite by the low solubility of calcium hydroxide. As such, when reacting chlorinated lime with a material comprising lithium, the lithium may be recovered as lithium chloride while a considerable amount of the calcium may be present as low soluble calcium hydroxide.

[0047] In some embodiments, the contacting step is at a temperature ranging from 20° C. to 100° C. for a duration ranging from 10 minutes to 10 hours. In some embodiments, the contacting step is at 100° C. for a duration ranging from

3 hours to 5 hours. In some embodiments, the contacting step is at 60° C. for a duration ranging from 3 hours to 5 hours. In some embodiments, the contacting step is at 25° C. for a duration ranging from 3 hours to 5 hours.

Solid/Liquid Separation:

[0048] In some embodiments, a process for removing lithium from a battery material comprises contacting the battery material with an aqueous medium comprising at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof to form a mixture, and separating in the mixture solids from liquids to obtain an aqueous solution comprising lithium ions. In some embodiments, a process for recycling lithium ion battery materials comprises mechanically comminuting at least one chosen from a lithium ion battery, lithium ion battery waste, lithium ion battery production scrap, lithium ion cell production scrap, lithium ion cathode active material, and combinations thereof to obtain a black mass, contacting the black mass with an aqueous medium comprising at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof, and separating solids from liquids to obtain an aqueous solution comprising lithium ions.

[0049] A reaction slurry containing insoluble residues from the black mass such as carbon, e.g., graphite, and solid calcium hydroxide obtained from the leaching step may be separated into a liquid solution and a solid residue by solid liquid separation. In some embodiments the lithium depleted solid residue may be collected. In some embodiments, calcium hydroxide is used to produce chlorinated lime.

[0050] In some embodiments, the separating step comprises at least one process chosen from filtration, decantation, centrifugation, flocculation, sedimentation and combinations thereof to separate the solids from the liquids.

Li/Ca Separation:

[0051] In some embodiments, a process for removing lithium from a battery material further comprises purifying the aqueous solution comprising lithium ions by at least one process chosen from adsorption, ion exchange, precipitation, crystallization, nanofiltration, concentration by water removal, drowning-out crystallization, re-dissolution of a lithium salt in an organic solvent, and combinations thereof. In some embodiments, a process for recycling lithium ion battery materials further comprises purifying the aqueous solution comprising lithium ions by at least one process chosen from adsorption, ion exchange, precipitation, crystallization, nanofiltration, concentration by water removal, drowning-out crystallization, re-dissolution of a lithium salt in an organic solvent, and combinations thereof.

[0052] A filtrate comprising lithium chloride, dissolved calcium hydroxide and some impurities e.g., aluminates, phosphates, fluorides, silicates etc. may be concentrated by evaporating water which may precipitate low soluble calcium salts like calcium aluminate, calcium fluoride, calcium silicate.

[0053] A lithium chloride solution may be further purified by, e.g., precipitation, ion exchange, adsorption reaction,

nanofiltration, by crystallizing lithium chloride, and/or solvent exchange of solvent using one or more solvents selective for dissolving lithium chloride. Such solvents may be alcohols, for example, methanol and ethanol. A lithium chloride solution may be purified by drowning-out crystallization by adding a less polar solvent to the aqueous solution such as ethanol, propanol, and/or isopropanol. Drowning-out crystallization processes are described in, e.g., Taboada, Maria Elisa, et al. "Process design for drowning-out crystallization of lithium hydroxide monohydrate." Chemical engineering research and design 85.9 (2007): 1325-1330.

[0054] A lithium/calcium separation may comprise nanofiltration, calcium precipitation as an oxalate, fluoride, phosphate, carbonate, and/or hydroxide, crystallization in water and/or methanol, solvent exchange, and/or ion exchange.

[0055] In some embodiments, calcium hydroxide is used to produce chlorinated lime.

Li/Na Separation:

[0056] In some embodiments, a process for removing lithium from a battery material further comprises separating lithium ions from sodium ions. In some embodiments, a process for recycling lithium ion battery materials further comprises separating lithium ions from sodium ions.

[0057] A process for separating lithium ions from calcium ions may also serve as a process for separating lithium ions from sodium ions. Similarly, a process for separating lithium ions from sodium ions may also serve as a process for separating lithium ions from calcium ions.

[0058] In some embodiments, a process for separating lithium ions from sodium ions is at least one chosen from lithium precipitation e.g. as carbonate, lithium solvent extraction, lithium adsorption, lithium ion exchange and combinations thereof.

Li Salt Transformation to LiOH:

[0059] In some embodiments, lithium salts may be transformed into the hydroxide form (LiOH). For example, Li_2CO_3 may be transformed to LiOH by reaction with $\text{Ca}(\text{OH})_2$.

[0060] In some embodiments, a process for removing lithium from a battery material further comprises subjecting the aqueous solution comprising lithium ions to at least one chosen from reaction with hydroxide, LiCl electrolysis, electro dialysis, and combinations thereof. In some embodiments, a process for recycling lithium ion battery materials further comprises subjecting the aqueous solution comprising lithium ions to at least one chosen from treatment with hydroxide, LiCl electrolysis, electro dialysis, and combinations thereof.

[0061] In some embodiments, a process for removing lithium from a battery material further comprises subjecting the aqueous solution comprising lithium ions to a chlor-alkali-electrolysis process to obtain lithium hydroxide and chlorine gas. In some embodiments a process for recycling lithium ion battery materials further comprises subjecting the aqueous solution comprising lithium ions to a chlor-alkali-electrolysis process to obtain lithium hydroxide and chlorine gas.

[0062] A lithium chloride solution may be subjected to chlor-alkali-electrolysis to obtain lithium hydroxide and chlorine gas. Some electrolysis processes are described, e.g., in RU2713360 and EP3589762. Resulting lithium hydroxide may be recovered and, if necessary, further purified. Chlorine gas can be collected, and, in a preferred embodiment, the chlorine gas is used to produce chlorinated lime. In another preferred embodiment recovered calcium hydroxide is used in the production of chlorinated lime. The calcium hydroxide may be separated from a solid residue by techniques such as graphite flotation, carrier flotation, and/or carrier magnetic separation.

LiOH·H₂O Crystallization:

[0063] In some embodiments, lithium hydroxide may be further purified by crystallization.

Exemplary Process:

[0064] FIG. 1 depicts an exemplary process for removing lithium from a battery material and/or an exemplary processes for recycling lithium ion battery materials (**100**). The material may be treated in an aqueous medium with calcium hypochlorite (**101**). Subsequent solid-liquid separation such as filtration, decantation, centrifugation, and/or sedimentation flocculation may be performed (**102**). A lithium depleted solid residue may be collected (**108**) and may comprise calcium salts such as calcium hydroxide. The liquid portion comprising lithium may be subjected to a Li/Ca separation (**103**) and a calcium salt may be collected (**109**). For example, lithium species and calcium species may be separated using, e.g. nanofiltration, calcium precipitation, crystallization in water and/or methanol, solvent exchange, and/or ion-exchange. Calcium species may be precipitated as an oxalate, fluoride, phosphate, carbonate, and/or hydroxide. Calcium species may be precipitated as a hydroxide by treatment with, e.g., LiOH, NaOH, and/or KOH. A lithium salt solution may be further subjected to a Li/Na separation (**104**) such as lithium precipitation e.g., as carbonate, solvent extraction, lithium absorption lithium ion exchange. The lithium salt may be transformed to LiOH (**105**) by, for example, reaction with $\text{Ca}(\text{OH})_2$, LiCl electrolysis, and/or electro dialysis. Optionally, Cl_2 from LiCl electrolysis may be recycled to produce calcium hypochlorite. Lithium hydroxide may subsequently be crystallized (**106**) to give a lithium salt such as $\text{LiOH}\cdot\text{H}_2\text{O}$ (**107**).

EMBODIMENTS

[0065] Without limitation, some embodiments of the disclosure include:

[0066] 1. A process for removing lithium from a battery material comprising contacting the battery material with an aqueous medium comprising at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof to form a mixture, and separating in the mixture solids from liquids to obtain an aqueous solution comprising lithium ions.

[0067] 2. The process according to embodiment 1, wherein the battery material comprises at least one chosen from lithiated nickel cobalt manganese oxide, lithiated

nickel cobalt aluminum oxide, lithium metal phosphate, lithium ion battery scrap, and black mass derived from a lithium ion battery.

[0068] 3. The process according to embodiment 1 or 2, wherein the battery material comprises lithium metal phosphate of formula Li_xMPO_4 wherein x is an integer greater than or equal to one, and M is chosen from metals, transition metals, rare earth metals, and combinations thereof.

[0069] 4. The process according to any one of embodiments 1 to 3, wherein the battery material comprises lithiated nickel cobalt manganese oxide of formula $\text{Li}_{1+x}(\text{Ni}_a\text{Co}_b\text{Mn}_c\text{M}^d)_{1-x}\text{O}_2$, wherein M^d is chosen from Mg, Ca, Ba, Al, Ti, Zr, Zn, Mo, V and Fe, $0 \leq x \leq 0.2$, $0.1 \leq a \leq 0.95$, $0 \leq b \leq 0.9$ (such as $0.05 \leq b \leq 0.5$), $0 \leq c \leq 0.6$, $0 \leq d \leq 0.1$, and $a+b+c+d=1$.

[0070] 5. The process according to any one of embodiments 1 to 4, wherein the battery material comprises lithiated nickel-cobalt aluminum oxides of formula $\text{Li}[\text{Ni}_h\text{CO}_i\text{Al}_j]\text{O}_{2+r}$, wherein h ranges from 0.8 to 0.90, i ranges from 0.1 to 0.3, j ranges from 0.01 to 0.10, and r ranges from zero to 0.4.

[0071] 6. The process according to any one of embodiments 1 to 5, wherein the battery material comprises nickel, cobalt, manganese, copper, aluminum, iron, phosphorus, or combinations thereof.

[0072] 7. The process according to any one of embodiments 1 to 6, wherein the battery material has a weight ratio ranging from 0.01 to 10, from 0.01 to 5, from 0.01 to 2, or from 0.01 to 1 of lithium to a total weight of nickel, cobalt, manganese, copper, aluminum, iron, and phosphorus.

[0073] 8. The process according to any one of embodiments 1 to 7, wherein at the contacting step, a weight ratio of the at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof to a total weight of the battery material ranges from 0.1 to 100, from 0.1 to 70, from 0.1 to 50, from 0.1 to 30, from 1 to 100, from 10 to 100, from 30 to 100, or from 50 to 100.

[0074] 9. The process according to any one of embodiments 1 to 8, wherein the contacting step is at a temperature ranging from 20°C . to 100°C . for a duration ranging from 10 minutes to 10 hours.

[0075] 10. The process according to any one of embodiments 1 to 9, wherein the separating step comprises at least one process chosen from filtration, decantation, centrifugation, sedimentation and combinations thereof to separate the solids from the liquids.

[0076] 11. The process according to any one of embodiments 1 to 10, further comprising purifying the aqueous solution comprising lithium ions by at least one process chosen from adsorption, ion exchange, precipitation, crystallization, nanofiltration, concentration by water removal, drowning-out crystallization, re-dissolution of a lithium salt in an organic solvent, and combinations thereof.

[0077] 12. The process according to any one of embodiments 1 to 11, further comprising subjecting the aqueous solution comprising lithium ions to a chlor-alkali-electrolysis process to obtain lithium hydroxide and chlorine gas.

[0078] 13. The process according to embodiment 12, wherein the chlorine gas is used to produce chlorinated lime and/or lithium hypochlorite.

[0079] 14. The process according to any one of embodiments 1 to 13, wherein calcium hydroxide is recovered from the solids.

[0080] 15. The process according to embodiments 14, wherein the calcium hydroxide is used to produce chlorinated lime.

[0081] 16. A process for recycling lithium ion battery materials comprising mechanically comminuting at least one chosen from a lithium ion battery, lithium ion battery waste, lithium ion battery production scrap, lithium ion cell production scrap, lithium ion cathode active material, and combinations thereof to obtain a black mass, contacting the black mass with an aqueous medium comprising the at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof, and separating solids from liquids to obtain an aqueous solution comprising lithium ions.

[0082] 17. The process according to any one of embodiments 1 to 16, wherein the at least one salt is calcium hypochlorite.

[0083] 18. The process according to embodiment 13, wherein the chlorinated lime and/or lithium hypochlorite produced from the chlorine gas obtained from the chlor-alkali-electrolysis is used for removing lithium from a battery material according to any one of embodiments 1 to 17.

[0084] 19. The process according to any one of embodiments 1 to 18, wherein an initial pH at the contacting step of the mixture is less than 11, less than 10.9, less than 10.8, less than 10.7, or less than 10.6.

[0085] 20. The process according to any one of embodiments 1 to 19, wherein a final pH at the contacting step of the mixture is less than 10, less than 9, or less than 8.

[0086] 21. The process according to any one of embodiments 1 to 20, wherein a pH during the contacting step of the mixture ranges from 5 to less than 11, less than 10.9, less than 10.8, less than 10.7, or less than 10.6.

[0087] 22. The process according to any one of embodiments 1 to 21, wherein the battery material and/or the black mass comprises less than 5 weight %, 1 weight %, or 0.1 weight % lithium carbonate, Li_2CO_3 , by total weight of the battery material and/or the black mass.

[0088] 23. The process according to any one of embodiments 1 to 22, wherein the battery material and/or the black mass comprises less than 5 weight %, 1 weight %, or 0.1 weight % lithium iron phosphate and iron phosphate by total weight of the battery material and/or the black mass.

[0089] Claims or descriptions that include “or” or “and/or” between at least one members of a group are considered satisfied if one, more than one, or all of the group members are present in, employed in, or otherwise relevant to a given product or process unless indicated to the contrary or otherwise evident from the context. The disclosure includes embodiments in which exactly one member of the group is present in, employed in, or otherwise relevant to a given product or process. The disclosure includes embodiments in

which more than one, or all the group members are present in, employed in, or otherwise relevant to a given product or process.

[0090] Furthermore, the disclosure encompasses all variations, combinations, and permutations in which at least one limitation, element, clause, and descriptive term from at least one of the listed claims is introduced into another claim. For example, any claim that is dependent on another claim can be modified to include at least one limitation found in any other claim that is dependent on the same base claim. Where elements are presented as lists, such as, e.g., in Markush group format, each subgroup of the elements is also disclosed, and any element(s) can be removed from the group. It should be understood that, in general, where the disclosure, or aspects of the disclosure, is/are referred to as comprising particular elements and/or features, embodiments of the disclosure or aspects of the disclosure consist, or consist essentially of, such elements and/or features. For purposes of simplicity, those embodiments have not been specifically set forth in haec verba herein. Where ranges are given, endpoints are included. Furthermore, unless otherwise indicated or otherwise evident from the context and understanding of one of ordinary skill in the art, values that are expressed as ranges can assume any specific value or sub range within the stated ranges in different embodiments of the disclosure, unless the context clearly dictates otherwise.

[0091] Those of ordinary skill in the art will recognize or be able to ascertain using no more than routine experimentation, many equivalents to the specific embodiments of the disclosure described herein. Such equivalents are intended to be encompassed by the following claims.

EXAMPLES

[0092] The following examples are intended to be illustrative and are not meant in any way to limit the scope of the disclosure.

Abbreviations

[0093]	% percent
[0094]	K ₂ CO ₃ potassium carbonate
[0095]	Na ₂ CO ₃ sodium carbonate
[0096]	Na ₂ B ₄ O ₇ sodium tetraborate
[0097]	p.a. grade pro analysis grade
[0098]	n.d. not determined
[0099]	Na ₂ S ₂ O ₈ sodium persulfate
[0100]	w % weight percent
[0101]	(NH ₄) ₂ S ₂ O ₈ ammonium persulfate
[0102]	Ca(ClO) ₂ calcium hypochlorite
[0103]	NaClO sodium hypochlorite
[0104]	NaOH sodium hydroxide
[0105]	Li lithium
[0106]	Ni nickel
[0107]	Co cobalt
[0108]	Mn manganese
[0109]	Cu copper
[0110]	Al aluminum
[0111]	Fe iron
[0112]	P phosphorus
[0113]	F fluorine
[0114]	Ca calcium

Elemental Analysis

[0115] Elemental analysis of lithium, calcium, and manganese was determined according to the following process.

[0116] The reagents used were deionized water, hydrochloric acid (36%), K₂CO₃—Na₂CO₃ mixture (dry), Na₂B₄O₇ (dry), and hydrochloric acid 50 vol.-% (1:1 mixture of deionized water and hydrochloric acid (36%)). All reagents were p.a. grade.

[0117] Samples were prepared using 0.2-0.25 g of the black mass weighed into a Pt crucible to which was applied a K₂CO₃—Na₂CO₃/Na₂B₄O₇ fusion digestion. The sample was burned in an unshielded flame and subsequently ashed in a muffle furnace at 600° C. The remaining ash was mixed with K₂CO₃—Na₂CO₃/Na₂B₄O₇ (0.8 g/0.2 g) and melted until a clear melt was obtained. The cooled melting cake was dissolved in 30 mL of water, and 12 mL of 50 vol.-% hydrochloric acid was added. The solution was filled up to a defined volume of 100 mL. Samples were prepared in triplicate, and a blank sample was prepared for reference purposes.

[0118] Li, Ca, and Mn within the obtained sample solution was determined by optical emission spectroscopy using an inductively coupled plasma (ICP-OES). An ICP-OES Agilent 5100 SVDV was used with the following characteristics: wavelengths: Li 670.783 nm; Ca 396.847 nm; Mn 257.610 nm; internal standard: Sc 361.383 nm; dilution factors: Li 100, Ca 10, Mn 100; calibration: external.

[0119] Elemental analysis of fluorine and fluoride was performed in accordance with DIN EN 14582:2016-12 with regard to the sample preparation for the overall fluorine content determination (waste samples); the detection method was an ion selective electrode measurement. DIN 38405-D4-2:1985-07 (water samples; digestion of inorganic solids with subsequent acid-supported distillation and fluoride determination using ion selective electrode).

[0120] Other metal impurities and phosphorous were determined analogously by elemental analysis using ICP-OES (inductively coupled plasma-optical emission spectroscopy) or ICP-MS (inductively coupled plasma-mass spectrometry). Total carbon was determined with a thermal conductivity detector after combustion.

Black Mass

[0121] Black mass was obtained by mechanical comminution of lithium ion batteries and subsequent separation of the black mass as a fine powder from the other constituents of the lithium ion batteries. The black mass had an elemental composition according to Table 1 determined by elemental analysis.

TABLE 1

	Li w %	Ni w %	Co w %	Mn w %	Cu w %	Al w %	Fe w %	P w %	F w %	Ca w %
black mass 1	2.5	12.4	2.9	3.5	1.2	1.4	0.08	0.31	1.9	0.04
black mass 2	3.7	9.3	5.9	14.0	0.9	2.8	0.04	0.7	4.4	0.01
black mass 3	2.8	6.9	4.6	12.2	0.76	2.1	0.04	0.61	4	0.007

Example 1

[0122] The black mass (30 g) was suspended in deionized water (200 g) and to this, calcium hypochlorite containing 65% active chlorine (Merck 211389) (30 g) was added in portions under stirring. After addition, the reactor content was heated to the desired temperature. After the reaction time, the reactor content was cooled to room temperature and filtered. The filter residue was washed with deionized water to obtain a combined filtrate and a filter residue and subsequently dried in vacuo at 70° C. overnight. Both the filtrate and filter residue were analyzed by elemental analysis. From the analytical data, the recovery of the elements was calculated. The results are summarized in Table 2.

then 83 g of 6 M hydrochloric acid was added. The pH-value dropped from 9 to 5 after which the pH-value of the solution stayed at 5. The experiment was stopped 5 h after the addition of the hydrochloric acid. The suspension was filtered, and the solid residue was washed with deionized water and dried. Elemental analysis of the filtrate and the solid residue indicated a lithium recovery of 71%. In the filtrate traces of Ni, Co, Cu and Fe were found.

Example 3

[0125] Sodium persulfate was used instead of sodium hypochlorite in a procedure similar to that of Example 2

TABLE 2

Example	Black mass	Weight black mass	Weight Ca(ClO) ₂	Weight water	Reaction temperature	Reaction duration	Recovery in filtrate	Content in filtrate (w %)	
no.	no.	g	g	g	° C.	h	Li %	Ca %	F %
2a	1	30	30	275	100	4	95	0.9	<0.1
2b	1	30	30	350	100	4	94	1.2	<0.1
2c	1	30	30	200	60	4	77	n.d.	n.d.
2d	1	30	30	275	60	4	88	n.d.	n.d.
2e	1	30	30	350	60	4	84	n.d.	n.d.
2f	1	30	30	275	25	4	54	n.d.	n.d.
2g	1	30	30	350	25	4	52	n.d.	n.d.
2h	2	30	30	200	100	4	73	n.d.	n.d.

[0123] The molar ratio Li to Cl used was 0.1 to 0.4. No base metal ions could be detected in the obtained filtrates. The pH-value was monitored during the experiment 2c. After the addition of calcium hypochlorite, the pH immediately rose from 6 to 10.5. Minutes after the addition of the hypochlorite, the pH-value was 7 and further decreased to a final value of 6.3 during the reaction. These changes in

using the reagents and reaction conditions provided in Table 3. The molar ratio between Li and persulfate was 0.1 to 0.07. In the filtrate of the experiment without sodium hydroxide addition also 0.36% Ni and 0.03% Co was detected. In the experiment with sodium hydroxide addition no base metal ions could be detected.

TABLE 3

Example	Black mass	Weight black mass	Weight Na ₂ S ₂ O ₈	Weight NaOH	Weight water	Reaction temperature	Reaction duration	Li recovery
no.	no.	g	g	g	g	° C.	h	in filtrate %
3a	1	30	15.5	0	200	100	4	84
3b	1	30	15.5	5.2	200	100	4	51

pH-value may indicate a more complex reaction scheme than the equations given in the discussion above.

Example 2

[0124] To 1066 g of a 15 w % NaClO-solution in water, 100 g of black mass 3 was added (molar ration Li to Cl 0.4 to 2.1). The mixture was heated to 50° C. under stirring and

Example 4

[0126] Ammonium persulfate was used instead of sodium hypochlorite in a procedure similar to that of Example 2 using the reagents and reaction conditions provided in Table 4. The molar ratio between Li and persulfate was 0.1 to 0.07. In the filtrate, 0.36% Ni and 0.03% Co was detected.

TABLE 4

Example no	Black mass no.	Weight black mass g	Weight (NH ₄) ₂ S ₂ O ₈ g	Weight NaOH g	Weight water g	Reaction temperature ° C.	Reaction duration h	Li recovery in filtrate %
4a	1	30	15.5	0	200	100	4	80

[0127] It was observed that calcium hypochlorite gives higher lithium recoveries compared to sodium hypochlorite or ammonium persulfates. In addition, the calcium hydroxide formed kept the pH-value of the reaction solution at a level high enough to avoid dissolution of base metals and low enough to keep the reaction going.

1. A process for removing lithium from a battery material comprising:

contacting the battery material with an aqueous medium comprising at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof to form a mixture, and

separating in the mixture solids from liquids to obtain an aqueous solution comprising lithium ions.

2. The process according to claim 1, wherein the battery material comprises at least one chosen from lithiated nickel cobalt manganese oxide, lithiated nickel cobalt aluminum oxide, lithium metal phosphate, lithium ion battery scrap, and black mass derived from a lithium ion battery.

3. The process according to claim 1, wherein the battery material comprises lithium metal phosphate of formula Li_xMPO₄ wherein x is an integer greater than or equal to one, and M is chosen from metals, transition metals, rare earth metals, and combinations thereof.

4. The process according to claim 1, wherein the battery material comprises lithiated nickel cobalt manganese oxide of formula Li1+x(NiaCobMncM1d)1-xO2, wherein

M1 is chosen from Mg, Ca, Ba, Al, Ti, Zr, Zn, Mo, V and Fe,

zero≤x≤0.2,

0.1≤a≤0.95,

zero≤b≤0.9, or 0.05<b≤0.5,

zero≤c≤0.6,

zero≤d≤0.1, and

a+b+c+d=1.

5. The process according to claim 1, wherein the battery material comprises lithiated nickel-cobalt aluminum oxides of formula Li[NihCoiAlj]O2+r, wherein

h ranges from 0.8 to 0.90,

i ranges from 0.1 to 0.3,

j ranges from 0.01 to 0.10, and

r ranges from zero to 0.4.

6. The process according to claim 1, wherein the battery material comprises nickel, cobalt, manganese, copper, aluminum, iron, phosphorus, or combinations thereof.

7. The process according to claim 1, wherein the battery material has a weight ratio ranging from 0.01 to 10, 0.01 to 5, 0.01 to 2, or 0.01 to 1 of lithium to a total weight of nickel, cobalt, manganese, copper, aluminum, iron, and phosphorus.

8. The process according to claim 1, wherein at the contacting step, a weight ratio of calcium hypochlorite salt to a total weight of the battery material ranges from 0.1 to 100.

9. The process according to claim 1, wherein the contacting step is at a temperature ranging from 20° C. to 100° C. for a duration ranging from 10 minutes to 10 hours.

10. The process according to claim 1, wherein the separating step comprises at least one process chosen from filtration, decantation, centrifugation, sedimentation, flocculation, and combinations thereof to separate the solids from the liquids.

11. The process according to claim 1, further comprising purifying the aqueous solution comprising lithium ions by at least one process chosen from adsorption, ion exchange, precipitation, crystallization, nanofiltration, concentration by water removal, drowning-out crystallization, re-dissolution of a lithium salt in an organic solvent, and combinations thereof.

12. The process according to claim 1, further comprising subjecting the aqueous solution comprising lithium ions to a chlor-alkali-electrolysis process to obtain lithium hydroxide and chlorine gas.

13. The process according to claim 12, wherein the chlorine gas is used to produce chlorinated lime and/or lithium hypochlorite.

14. The process according to claim 1, wherein calcium hydroxide is recovered from the solids.

15. The process according to claim 14, wherein the calcium hydroxide is used to produce chlorinated lime.

16. A process for recycling lithium ion battery materials comprising:

mechanically comminuting at least one chosen from a lithium ion battery, lithium ion battery waste, lithium ion battery production scrap, lithium ion cell production scrap, lithium ion cathode active material, and combinations thereof to obtain a black mass,

contacting the black mass with an aqueous medium comprising at least one salt chosen from calcium hypochlorite, lithium hypochlorite, and combinations thereof, and

separating solids from liquids to obtain an aqueous solution comprising lithium ions.

17. The process according to claim 1, wherein the at least one salt is calcium hypochlorite.

18. The process according to claim 13, wherein the chlorinated lime and/or lithium hypochlorite produced from the chlorine gas obtained from the chlor-alkali-electrolysis is used for removing lithium from the battery material.

19. The process according to claim 1, wherein an initial pH at the contacting step of the mixture is less than 11.

20. The process according to claim 1, wherein a final pH at the contacting step of the mixture is less than 10.

21. The process according to claim 1, wherein a pH during the contacting step of the mixture ranges from 5 to less than 11.

22. The process according to claim 1, wherein the battery material and/or the black mass comprises less than 5 weight

% lithium carbonate, Li_2CO_3 , by total weight of the battery material and/or the black mass.

23. The process according to claim 1, wherein the battery material and/or the black mass comprises less than 5 weight % lithium iron phosphate and iron phosphate by total weight of the battery material and/or the black mass.

* * * * *